

REPORT DOCUMENTATION PAGE

READ INSTRUCTIONS
BEFORE COMPLETING FORM

1. REPORT NUMBER No. 53	2. GOVT ACCESSION NO.	3. RECIPIENT'S CATALOG NUMBER
4. TITLE (and Subtitle) Free Electron Lasers and Magnetic Materials		5. TYPE OF REPORT & PERIOD COVERED Technical Report 10/01/84 - 09/30/85
6. PERFORMING ORG. REPORT NUMBER		
AUTHOR(s) Luis R. Elias, Isidoro Kimel, and Gerald Ramian		8. CONTRACT OR GRANT NUMBER(s) N00014-80-C-0308
PERFORMING ORGANIZATION NAME AND ADDRESS University of California Quantum Institute Santa Barbara, CA 93106		10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS 61153N; RR011-07-06; NR603-001
CONTROLLING OFFICE NAME AND ADDRESS ONR 1030 E. Green St. Pasadena, CA 91106		12. REPORT DATE 1985
14. MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office)		13. NUMBER OF PAGES
15. SECURITY CLASS. (of this report) Unclassified/Unlimited		15a. DECLASSIFICATION/DOWNGRADING SCHEDULE
16. DISTRIBUTION STATEMENT (of this Report) Approved for public release; distribution.		
17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report)		
18. SUPPLEMENTARY NOTES Proceedings of the International Conference on Magnetism, 1985.		
19. KEY WORDS (Continue on reverse side if necessary and identify by block number) FEL, Magnetic		
20. ABSTRACT (Continue on reverse side if necessary and identify by block number) Free Electron Laser (FELs), offering coherent, tunable, high power submillimeter radiation, open exciting areas of magnetic materials research. At the same time, FELs have benefited from magnetic materials research - specifically the modern development of Rare Earth Cobalt and Neodymium-Iron-Boron permanent magnet materials. Application of these materials to a new type of short period FEL undulator is described.		

DTIC
ELECTE
MAY 21 1990
D CS D

ADVISORY GROUP
RECEIVED
FEB 10 1986
ON ELECTRON DEVICES

90 05 17 072

AD-A221 739

WIG FILE COPY

FREE ELECTRON LASERS AND MAGNETIC MATERIALS (*)

L. Elias, I. Kimeel, and G. Ramian
Quantum Institute, University of California,
Santa Barbara, Ca. 93106

ABSTRACT

Free Electron Lasers (FELs), offering coherent, tunable, high power submillimeter radiation, open exciting areas of magnetic materials research. At the same time, FELs have benefited from magnetic materials research - specifically the modern development of Rare Earth Cobalt and Neodymium-Iron-Boron permanent magnet materials. Application of these materials to a new type of short period FEL undulator is described.

INTRODUCTION

Free Electron Lasers (FELs) are of interest to the magnetics community both as a research tool and as an interesting application of permanent magnet materials. One such application will be the subject of this paper.

As a research tool of particular interest to the magnetics community, the FEL's unique high power and tunability throughout the submillimeter and far infrared wavelengths are useful, for example, for spectroscopy of magnetic resonances, generation of spin waves in large band-gap ferro-magnetic systems, and the study of non-linear magnon modes.

On the other hand, the development of FELs has benefited enormously from the development of modern magnetic materials - specifically Rare Earth Cobalt magnets and, more recently, Neodymium-Iron-Boron materials. FEL undulators employing these materials have, however, been limited to centimeter periods primarily due to the difficulty of handling tiny individual magnets which develop large physical force. Non-traditional undulator geometries that produce millimeter period fields suitable for the generation of far infrared radiation with compact low voltage accelerators are discussed. An analytical evaluation of the fields produced by these configurations is presented.

MATERIALS

The field reversal pattern of an FEL undulator (see Fig. 1) results in an inherently high reluctance structure and consequently, a large demagnetizing force at most points within the structure. Prior to the advent of Samarium-Cobalt materials with coercive force $H_{ci} > 10^4$ Oe, permanent magnet undulators of, for example, Alnico 5 ($H_{ci} \sim 10^3$ Oe) would have produced impractically feeble fields. More recently, Neodymium-Iron-Boron materials with residual fields as high as 12.5 KG [1] have increased the attainable peak field by ~25% over Samarium-Cobalt, while improved mechanical properties such as brittleness and tensile strength have eased design limitations. Mechanical strength problems in fact necessitated the sheathing of each individual magnet of the UCSB undulator with stainless steel (magnet dimensions: 8.5 X 8.5 X 100 MM).




Fig. 1 Schematic representation of an FEL. A relativistic electron beam is transversely accelerated by a periodically reversing magnetic field. Electromagnetic energy emitted by the electrons is captured and stored between mirrors of a resonator.

MICRO-UNDULATORS

FELs generate light of wavelength $\lambda = \lambda_0 / 2\gamma^2$, where λ_0 = undulator period and γ , the relativistic mass ratio, is $qV/m_0c^2 + 1$. The present UCSB FEL generates light between 400 μ and 110 μ corresponding to energies between 3 and 6 MEV. Generation of submillimeter wavelengths with smaller electrostatic accelerators ($E = 1$ to 2 MEV) or generation of infrared wavelengths with higher voltage machines, requires undulator periods in the millimeter range rather than the centimeter range (3.6 CM) of the present UCSB machine.

Conventional undulators, such as the Halbach configuration used in the UCSB FEL, consist of individual magnets with successively rotated magnetic orientation. Recognition of the difficulty of handling individual magnets of the dimensions required for a short period undulator motivated the development of alternate configurations that we refer to as "Micro-undulators" [2]. These structures consist of grooves ground in large blocks of material (see Fig. 2a and 2b). Periods as short as 1MM using blocks of approximately 5 X 5 CM appear practical. The field orientation of the blocks of Fig. 2a forces flux return paths to exist around the edges and ends, resulting in deleterious transverse quadrupole fields and axial end fields. This configuration is considered because blocks of this orientation are readily available. The configuration of Fig. 2b not only avoids the quadrupole fields but its end fields can be shaped to provide electron beam injection dipoles. "Cross-field" material of this type is presently available only in Samarium-Cobalt and with lower Br.




Fig. 2 Micro-undulator configurations

FIELD ANALYSIS

A full three dimensional analysis of the Micro-undulator fields of Fig. 2a, based on the assumption of an ideal magnet i.e., uniform M with delta function discontinuities at each surface, yields

$$B_y = \frac{2\mu_0 M}{\pi} \sum_{n \text{ odd}} \frac{(-1)^{(n-1)/2}}{n} (1 - e^{-2\pi n h / \lambda_0}) e^{-n\pi g / \lambda_0} \cosh\left(\frac{2\pi n y}{\lambda_0}\right) \sin\left(\frac{2\pi n z}{\lambda_0}\right) \left[1 - \frac{2\lambda_0}{\pi^2 g} \left(e^{-\pi \frac{(w+2x)^2}{2\lambda_0 g}} + e^{-\pi \frac{(w-2x)^2}{2\lambda_0 g}} \right) \right] \quad (1)$$

$$B_z = \frac{2\mu_0 M}{\pi} \sum_{n \text{ odd}} \frac{(-1)^{(n-1)/2}}{2} (1 - e^{-2\pi n h / \lambda_0}) e^{-n\pi g / \lambda_0} \sinh\left(\frac{2\pi n y}{\lambda_0}\right) \cos\left(\frac{2\pi n z}{\lambda_0}\right) \left[1 - \frac{2\lambda_0}{\pi^2 g} \left(e^{-\pi \frac{(w+2x)^2}{2\lambda_0 g}} + e^{-\pi \frac{(w-2x)^2}{2\lambda_0 g}} \right) \right] \quad (2)$$

$$B_x = \frac{8\mu_0 M}{\pi^2 g^2} \sum_{n \text{ odd}} \frac{(-1)^{\frac{n-1}{2}}}{2} (1 - e^{-\frac{2\pi n h}{\lambda_0}}) e^{-\frac{n\pi g}{\lambda_0}} \cosh\left(\frac{2\pi n y}{\lambda_0}\right) \sin\left(\frac{2\pi n z}{\lambda_0}\right) \left[(w-2x)e^{-\frac{\pi(w-2x)^2}{2\lambda_0 g}} - (w+2x)e^{-\frac{\pi(w+2x)^2}{2\lambda_0 g}} \right] \quad (3)$$

Fig.3 plots B_y as a function of y for several harmonics (eqn. 1). Odd harmonic components, though larger than those of the Halbach configuration, are still quite reasonable. For example a period of 4.5 MM and a gap of 3 MM results in a .5% third harmonic.




Fig. 3 Plot of B_y and its harmonic content as a function of y

CONCLUSION

The micro-undulator concept represents an application of modern magnetic materials that promises compact low voltage electrostatic accelerator FELs for the submillimeter region and infrared FELs with higher voltage electrostatic machines.

REFERENCES

- [1] IG Technology Inc., Valparaiso, Indiana
- [2] L.Elias and G.Ramian, "Micro-Undulator FEL Technology," PROCEEDINGS OF THE INTERNATIONAL CONFERENCE ON LASERS '84, San Francisco, Ca.

* Research supported under
ONR contract N00014-80-C-0308



ADDITIONAL FOR	
THIS GRA&I	<input checked="" type="checkbox"/>
DTIC TAB	<input type="checkbox"/>
Unannounced	<input type="checkbox"/>
Justification	
By	
Distribution	
Availability Codes	
Dist	Avail and/or Special
A-1	